
TOPP & CO.

GREAT BRITAIN

Exquisite Architectural Metalwork



Manganese Bronze Ogee Profile OGI

Lengths: 5m (16ft) and 2.5m (8 ft) Weight per 5m length: 14.45kg Price per length: On application

Tolerances A ±0.50
B ±0.35

Supplied unfinished

Fabrication Properties

Excellent hot working, temperature range	680° - 730° C
Less suitable for cold working, max reduction	15%
Machining, as percentage of CuZn39Pb3, (100%)	Fair, 40%
Annealing temperature range	550° - 650° C
Stress relieving temperature range	280° - 350° C
Soldering	Good
Brazing	Good
Oxy-acetylene welding	Excellent
Gas-shielded arc welding	Excellent
Resistance welding, butt	Fair
Resistance welding, seam and spot	Not recommended

Joining

Manganese bronze can be brazed, TIG welded or silver soldered. If you decide to braze or TIG weld, we would recommend you use the same material in brazing or welding rods. Because there is zinc in the profile, if you braze or TIG weld you will always get a slight difference in colour between the weld and the rest of the profile. The best option is to use silver solder. Make a butt joint as tight as possible before soldering it. When the soldering is cleaned you will only see a very tiny line on the joint.

Polishing

Manganese bronze profiles polish exactly the same as any other bronze product.

Patinating

If you want to patinate the manganese bronze profile, we suggest using a chemical called Curator Antique Fluid. You can get different types of colouring - black, brown and bronze.

When patination is applied, wait for the desired finish, then you need to stop the oxidation by washing the profile with clean water. You will have to let it dry and make sure there is no moisture. Then you have to seal the patination with Jade oil and a lacquer. Be careful not to use oil with strong solvent in it as it will remove the patination.

If you need the chemical composition for this profile please ask.



GREAT BRITAIN

Unit 5,The Airfield • Tholthorpe • North Yorkshire • YO61 IST • United Kingdom +44 (0)1347 833173 • enquiry@toppandco.com• www.toppandco.com